



Zytel®

nylon resin

Zytel® 70G33L NC010 Glass Reinforced Nylon Resin

Zytel® 70G33L NC010 is a 33% glass reinforced general purpose PA 66 resin.

Property	Test Method	Units	Value	
			DAM	50%RH
Mechanical				
Tensile Strength	ASTM D 638	MPa (kpsi)		
-40C (-40F)			214 (31.0)	207 (30.0)
23C (73F)			186 (27.0)	124 (18.0)
77C (170F)			110 (16.0)	86 (12.5)
Stress at Break	ISO 527-1/-2	MPa (kpsi)	193 (28.0)	126 (18.3)
Elongation at Break	ASTM D 638	%	3	4
Strain at Break	ISO 527-1/-2	%	3.2	5
Tensile Modulus	ISO 527-1/-2	MPa (kpsi)	10500 (1520)	7000 (1015)
Shear Strength	ASTM D 732	MPa (kpsi)	86 (12.5)	
Poisson's Ratio			0.39	
Flexural Modulus	ASTM D 790	MPa (kpsi)	8965 (1300)	6205 (900)
Flexural Modulus	ISO 178	MPa (kpsi)	9100 (1320)	6205 (900)
Flexural Strength	ASTM D 790	MPa (kpsi)	262 (38.0)	
Deformation Under Load	ASTM D 621	%		
50C (122F), 13.8MPa (2000psi)			0.8	
Izod Impact	ASTM D 256	J/m (ft lb/in)	117 (2.2)	133 (2.5)
Notched Izod Impact	ISO 180/1A	kJ/m2		
-40C (-40F)			9	10
-30C (-22F)				10
23C (73F)			11	15
Unnotched Izod Impact	ISO 180/1U	kJ/m2		
-30C (-22F)				70
23C (73F)				90
Notched Charpy Impact	ISO 179/1eA	kJ/m2		
-40C (-40F)			9	10
-30C (-22F)			10	10
23C (73F)			12	16
Unnotched Charpy Impact	ISO 179/1eU	kJ/m2		
-30C (-22F)			85	70
23C (73F)			95	100

Contact DuPont for MSDS, general guides and/or additional information about ventilation, handling, purging, drying, etc.
Mechanical properties measured at 23°C (73°F) unless otherwise stated.

990209VC4

The data listed here fall within the normal range of product properties but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligation or liability for any advice furnished by it or for results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a license to operate under, or a recommendation to infringe, any patent of DuPont or others. DuPont warrants that the use or sale of any material which is described herein and is offered for sale by DuPont does not infringe any patent covering the material itself, but does not warrant against infringement by reason of the use thereof in combination with the other materials or in the operation of any process. CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement", H-50102.

Dial DuPont First (800) 441-0575 • Automotive Inquiries (800) 533-1313

Zytel® 70G33L NC010

Property	Test Method	Units	Value	
			DAM	50%RH
Thermal				
Heat Deflection Temperature 0.45MPa (66psi) 1.8MPa (264psi)	ASTM D 648	°C (°F)	261 (502) 249 (480)	
Deflection Temperature 1.80MPa	ISO 75-1/-2	°C (°F)	254 (489)	
CLTE, Flow -40 - 23C (-40 - 73F) 23 - 55C (73 - 130F) 55 - 160C (130 - 320F)	ASTM E 831	E-4/C (E-4/F)	0.24 (0.13) 0.18 (0.10) 0.13 (0.07)	
CLTE, Transverse -40 - 23C (-40 - 73F) 23 - 55C (73 - 130F) 55 - 160C (130 - 320F)	ASTM E 831	E-4/C (E-4/F)	0.65 (0.36) 0.83 (0.46) 1.37 (0.76)	
Melting Point	ASTM D 3418	°C (°F)	262 (504)	
Melting Temperature	ISO 3146C	°C (°F)	263 (505)	
Electrical				
Surface Resistivity 1mm	IEC 93	ohm	1E12	
Relative Permittivity 1E2 Hz, 1mm 1E6 Hz, 1mm	IEC 250		4.2 3.9	
Volume Resistivity 1mm	ASTM D 257 IEC 93	ohm cm ohm cm	1 E15 1E15	
Dielectric Strength, Short Time	ASTM D 149	kV/mm (V/mil)	20.9 (530)	
Dielectric Strength, Step by Step	ASTM D 149	kV/mm (V/mil)	17.3 (440)	
Dielectric Constant 1E3 Hz 1E6 Hz	ASTM D 150		4.5 3.7	
Dissipation Factor 1E3 Hz 1E6 Hz	ASTM D 150		0.02 0.02	
Dissipation Factor 1E2 Hz, 1mm 1E6 Hz, 1mm	IEC 250	E-4	90 150	
Arc Resistance	ASTM D 495	s	135	
CTI	UL 746A	V	>600	
Flammability				
Flammability Classification 0.71mm 1.5mm 3.0mm	UL94		HB HB HB	
Limited Oxygen Index	ISO 4589	%	24	
High Voltage Arc Tracking Rate	UL 746A	mm/min (in/min)	32.2 (1.27)	
Hot Wire Ignition	UL 746A	s	9	

Contact DuPont for MSDS, general guides and/or additional information about ventilation, handling, purging, drying, etc.
Mechanical properties measured at 23°C (73°F) unless otherwise stated.

990209VC4

The data listed here fall within the normal range of product properties but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligation or liability for any advice furnished by it or for results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a license to operate under, or a recommendation to infringe, any patent of DuPont or others. DuPont warrants that the use or sale of any material which is described herein and is offered for sale by DuPont does not infringe any patent covering the material itself, but does not warrant against infringement by reason of the use thereof in combination with the other materials or in the operation of any process. CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement", H-50102.

Dial DuPont First (800) 441-0575 • Automotive Inquiries (800) 533-1313

Zytel® 70G33L NC010

Property	Test Method	Units	Value	
			DAM	50%RH
Temperature Index				
RTI, Electrical	UL 746B	°C		
0.71mm			105	
1.5mm			120	
3.0mm			120	
RTI, Mechanical with Impact	UL 746B	°C		
0.71mm			65	
1.5mm			105	
3.0mm			105	
RTI, Mechanical without Impact	UL 746B	°C		
0.71mm			105	
1.5mm			120	
3.0mm			120	
Other				
Specific Gravity	ASTM D 792	kg/m3 (g/cm3)	1.38	
Density	ISO 1183		1390 (1.39)	
Hardness, Rockwell Scale M	ASTM D 785		101	
Taber Abrasion	ASTM D 1044	mg		14
CS-17 Wheel, 1kg, 1000 cycles				
Humidity Absorption	ISO 62, Similar to	%		
Equilibrium 50%RH			1.7	
Water Absorption	ASTM D 570	%		
Immersion 24h			0.7	
Saturation			5.4	
Water Absorption	ISO 62, Similar to	%		
Saturation, immersed			5.7	
Mold Shrinkage		%		
Flow, 3.2mm (0.126in)			0.2	
Molding Shrinkage	ISO 294-4	%		
Normal, 2.0mm			1.1	
Parallel, 2.0mm			0.4	
Processing				
Melt Temperature Range		°C (°F)	290-305 (550-580)	
Mold Temperature Range		°C (°F)	65-120 (150-250)	
Processing Moisture Content		%	<0.20	

Contact DuPont for MSDS, general guides and/or additional information about ventilation, handling, purging, drying, etc.
Mechanical properties measured at 23°C (73°F) unless otherwise stated.

990209VC4

The data listed here fall within the normal range of product properties but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligation or liability for any advice furnished by it or for results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a license to operate under, or a recommendation to infringe, any patent of DuPont or others. DuPont warrants that the use or sale of any material which is described herein and is offered for sale by DuPont does not infringe any patent covering the material itself, but does not warrant against infringement by reason of the use thereof in combination with the other materials or in the operation of any process. CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement", H-50102.

Dial DuPont First (800) 441-0575 • Automotive Inquiries (800) 533-1313